

RG 104, Sequence 27

8NN-104-86-027, Register of All Gold &
Silver Assays, 1905 - 1971.

Assayer's Register of Gold Ingots, 1906-1907

Form No. 324 A


ASSAYER'S REGISTER

OF

GOLD INGOTS

MINT U. S. DENVER

Sold 442



ASSAYER'S REGISTER OF GOLD INGOTS.

2-2220

DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.		FINESS.
Feb 21	1	899.99 899.76	899 87	Mar 14	32		899 9
"	2	899.78 899.87	899 82		33		899 8+
" 24	3		899 8+		34		899 7
	4		899 7	" 22	35		899 19
	5		899 9	" 23	36		899 9
27	6		900 +		37		899 8
Mar 1	7		900 +		38		899 9
	8	899.8 900.	899 9		39		899 5
	9	900.1 899.9	900	24	40		900 06
	10		899 8		41		899 8
5	11		900 1+	28	42		899 9
8	12		900 +		43		899 8
	13		899 7+		44		899 8
	14		899 9	29	45		899 8
	15		899 8+		46		899 8
	16		899 8+	30	47		899 8
	17		899 9+		48		899 8
	18		899 9+		49		899 8
9	19		899 9+	31	50		899 8
	20		900 +		51		899 8
	21		899 8+		52		899 9
Mar 10	22		899 84	April 2	53		899 8
	23		899 95		54		899 8
	24		900 04	3	55		899 8
	25		900 04		56		899 9
	26		899 9		57		899 9
	27		899 8		58		899 9
" 12	28		899 8	5	59		899 8
	29		899 7		60		899 8
	30		899 7		61		899 9
	31		900		62		899 7

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
April 6	63	899 9	April 18	95	899 8+
	64	899 7		96	899 7+
	65	899 5	19	97	899 8+
	66	899 8		98	899 9+
	67	899 7		99	899 9
7	68	899 8		100	899 5
	69	899 8	20	101	899 9+
	70	899 7+		102	899 7
9	71	899 9		103	899 7+
	72	899 8+		104	899 7+
	73	899 9	21	105	899 7
9	74	899 7		106	899 7+
	75	899 9		107	899 8
	76	899 8		108	899 7+
10	77	899 9	23	109	899 9
	78	899 8		110	899 9
11	79	899 8		111	899 8+
	80	899 7	24	112	899 7+
	81	899 8		113	899 7+
13	82	899 8		114	899 7+
	83	899 9		115	899 8+
	84	899 8		116	899 8+
14	85	899 9	24	117	899 9
	86	899 8		118	899 7
	87	899 7		119	899 9
	88	899 8	25	120	899 7
17	89	899 8		121	899 8
	90	899 7+	26	122	899 9+
	91	899 8		123	899 8+
18	92	899 7		124	899 5
	93	899 7+		124	899 7
	94	899 7+			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
April 26	125	899 8+	May 5	156	899 9
	126	899 8+		157	899 7
	127	899 7+	9	155	899 8
27	128	899 8+		159	899 8
	129	899 7		160	899 5
28	130	899 9		161	900
	131	899 7		162	899 5
	132	899 5	10	163	899 9
	133	899 8		164	899 9
	134	900		165	899 5
	135	899 9+		166	899 9
30	136	899 9		167	899 5
May 1	137	899 7+		168	899 9
	138	899 7+	11	169	899 8
	139	899 9		170	899 9
	140 ✓	899 5		171	899 5
" 3	141	899 8+		172	899 9
	142	899 7		173	899 5
	143	899 7		174	CONDENED.
	144	899 8+		175	899 7
" 4	145	899 9		176	899 5
	146	899 7	12	177	899 7
	147	899 5		178	899 5
	148	899 9	13	179	CONDENED.
5	149	899 9+		180	899 8
	150	899 7		181	900
	151	900 0+		182	899 5
	152	899 7		183	899 9
7	153	899 7		184	899 9
	154	899 9+	15	185	899 5
	155	899 9+		186	899 5

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
May 15	187	899 5	May 23	219	599 7
	188	899 5	24	220	899 5
16	189	899 7		221	899 7
	190	899 5		222	899 7
	191	899 5		223	899 5
	192	899 9	25	224	899 5
	193	899 5		225	899 5
	194	899 5		226	899 7
17	195	899 5		227	899 7
	196	899 5		228	899 5
	197	899 7		229	899 9
	198	899 7	26	230	899 8
18	199	899 5		231	899 8
	200	899 5		232	899 7
	201	899 7		233	899 5
	202	899 5	27	234	900
19	203	899 9		235	899 7
	204	899 7	28	236	899 7
	205	899 8		237	899 5
	206	899 7		238	899 5
	207	899 9		239	899 7
20	208	899 7	29	240	899 5
	209	899 9		241	899 5
	210	899 5		242	899 7
	211	899 7		243	899 5
22	212	900 1		244	899 5
	213	899 9		245	899 9
	214	899 7	June 1	246	899 9
	215	899 5		247	899 7
23	216	899 5	" 4	248	899 8
	217	899 7		249	899 5
	218	899 7		250	899 7

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1906					
June 5	251	899 7			
	252	899 5			
" 6	253	899 7			
	254	899 7			
	255	899 7			
	256	899 7			
" 7	257	899 7			
	258	899 7			
	259	899 9			
	260	899 8			
" 8	261	899 9			
	262	899 8			
	263	899 9			
" 9	264	899 8			
	265	899 9			
" "	266	899 9			
	267	899 7			
" 14	268	899 8			
	269	899 9			
	270	899 9			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1906					
July 14	1	899 7			
	2	899 7			
" 16	3	899 7			
	4	899 9			
17	5	900 -			
18	6	899 9.			
	7	899 9			
19	8	899 8			
20	9	899 7.			
21	10	899 8			
"	11 ✓	899 8			
23	12.	899 9.			
"	13	899 9.			
"	14	899 8			
24	15	899 9			
25	16	899 8			
"	17	899 9.			
26	18	899 8			
	19 ✓	899 9.			
27	20	899 9			
	21	899 9			
28	22	899 9			
	23	899 9			
30	24	899 9			
	25	899 9			
	26	900 +			
Aug 1.	27	900 1+			
	28	900 -			
	29	900 -			
2	30	900 -			
	31	900 -			
3	32	900 1			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	NO. OF MELT.	FINESS.	DATE	NO. OF MELT.	FINESS.
Aug 3	33	899 8	Aug 12	65	599 9
4	34	899 9			
	35	899 9			
6	36	899 9			
	37	900 -			
7	38	899 9			
	39	899 9			
8	40	900 -			
	41	899 9			
9	42	900 -			
10	43	900 14			
	44	899 9			
	45	899 8			
11	46	900 1			
	47	899 9			
12	48	899 9			
	49	899 8			
14	50	900 -			
	51	899 9			
15	52	899 9			
	53	900 -			
	54	899 9			
	55	899 9			
	56	899 8			
	57	899 9			
	58	899 8			
	59	899 9			
	60	899 9			
21	61	899 8			
	62	899 9			
	63	899 8			
22	64	891 4			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.		
1906							
Aug. 24. 1906	65	899	9	Dec 12	96	899	8
	66	899	9		97	899	9
	67	899	9		98	899	9
	68	899	8		99	899	8
	69	899	9	13	100	899	8
	70	899	9		101	899	8
Nov 28	71	899	9		102	899	8
	72	899	8		103	899	8
	73	899	8		104	899	8
30 th	74	899	8		105	899	8
	75	899	8	14	106	899	8
	76	899	9		107	899	8
Dec 3 rd	77	899	8		108	899	7
	78	899	7		109	899	9
	79	899	7	28	110	900	
	80	899	8		111	900	
	81	899	7		112	899	9
	82	899	9		113	900	
	83	899	8		114	900	
4	84	899	7		115	900	
	85	899	7		116	900	
	86	900			117	900	
	87	900		Jan 4.	118	899	9
8	88	899	9		119	900	1
	89	899	8		120	900	
	90	899	9		121	900	
	91	900			122	900	
10	92	899	9		123	900	
	93	899	9	Jan 5.	124	899	9
	94	899	9		125	899	9
	95	900			126	899	8
					127	899	9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	No. OF MELT.		FINENESS.	DATE	No. OF MELT.		FINENESS.
Jan. 5	128	899	899 8	1-17	160		899 9
	129		899 8		161		899 9
7.	130		899 9		162		900
	131		899 9 1/2		163		899 8
9	132		899 8		164		899 9
	133		899 9	1-18	165		899 8
	134		899 9		166		899 8
	135		Condenn		167		899 9
10	136		899 9		168		899 8
	137		899 9	1-19	169		899 9
	138		899 9		170		899 8
	139		900 -		171		899 8
11	140		899 9		172		899 8
	141		899 8	21	173		899 8
	142		899 9		174		899 7
	143		899 8		175		899 9
	144		899 8		176		899 9
12	145		899 9		177		900 -
	146		899 8		178		899 9
	147		899 8		179		900 +
	148		899 9		180		899 9
14	149		899 8	1-23	181		900
	150		899 9		182		899 9
	151		899 9		183		899 9
	152		899 9.		184		900
16	153		899 8	1-26	185		899 9
	154		900		186		899 8
	155		900		187		899 8
	156		899 8		188		899 7
1-17	157		899 9	1-29	189		899 8
	158		899 9		190		899 8
	159		899 8		191		899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
Jan 29	192	899 9.			
1 - 30	193	900 -			
	194	899 9			
	195	899 9			
	196	899 9			
	197	900			
	198	900			
	199	900			
	200	900			
Feb 1.	201	899 9			
	202	900 -			
	203	899 9			
	204	899 9.			
2 - 2	205	899 9			
	206	899 8			
	207	899 9+			
	208	899 9+			
2 - 4	209	900 -			
	210	900 -			
	211	899 8			
	212	899 9.			
2 - 5	213	899 9+			
	214	899 9			
	215	900 -			
	216	900 +			
	217	900			
	218	899 9			
	219	900			
	220	899 9			
7	221	899 9+			
	222	900			
	223	899 8+			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1907 July 7	224	900	7-15	255	900
8	225	900		256	899 8
	226	900		257	899 9
	227	900		258	899 9
	228	900		259	899 9+
9	229	899 8+		260	899 8+
	230	899 9	16	261	899 9
	231	899 9		262	899 8+
	232	899 9		263	899 9
	233	899 9+		264	899 8
11	234	899 8		265	899 8
	235	899 9	July	266	899 8
	236	899 8		267	899 8+
	237	899 8		268	899 8+
	238	899 8		269	899 7+
12	239	899 8		270	899 8
	240	899 8+		271	899 8
	241	899 8		272	899 8+
	242	899 9		273	899 8
	243	CONDENED. 895 8		274	899 8
13	244	899 9		275	899 7+
	245	900		276	899 8
	246	899 9		277	899 7+
	247	899 9		278	899 7+
	248	899 9		279	899 8
	249	900		280	899 7+
14	250	899 9+		281	899 7+
	251	899 8		282	899 8+
	252	899 9		283	899 8+
	253	899 9		284	899 8
	254	900			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1907.					
Feb 8	285	900	5-6	313	900
	286	899 9		314	900 ✓
	287	899 9		315	899 7 ✓
	288	900		316	899 5
Feb 9	289	899 8 +	5/28.	317	900
	290	899 8		318	899 9
	291	899 8 +		319	899 9.
	292	899 9			
	293	899 9			
Feb 11	294	899 9			
	295	900			
	296	900			
	297	899 9 +			
Mar 22	298	900			
	299	899 8			
	300	899 8			
	301	899 9			
	302	899 8			
	303	899 8			
	304	899 8			
	305	899 8			
	306	899 8			
	307	899 8			
	308	899 7			
	309	899 7			
	310	899 6 1/2			
	311	899 4 1/2			
	312	899 6 1/2			
	310	899 9			
	311	899 9			
	312	899 7			
	310	899 9			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1907					
Aug 26	1	✓ 899 5	9-18	33	✓ 599 9
	2	✓ 899 7		4	✓ 900 0
	3	✓ 899 7		5	✓ 899 7
	4	✓ 899 5		6	✓ 899 9
Aug 29	5	✓ 899 8		7	✓ 900 0
	6	✓ 899 5	9-24	8	✓ REMELT.
	7	✓ 899 9		9	✓ REMELT.
	8	✓ 899 5		40	✓ 899 9
	9	✓ 899 5		1	✓ 899 9
	10	✓ 899 5		2	✓ 900 1
	1	✓ 899 7		3	✓ 900
	2	✓ 899 7		4	✓ 899 9
Sept 3	3	✓ 899 9		5	✓ 899 9
	4	✓ 899 5		6	✓ 899 9
	5	✓ 899 5		7	✓ 899 9
	6	✓ 899 5		8	✓ 900
	7	✓ 899 5		9	✓ 899 9
	8	✓ 899 9	9-25	50	✓ 899 9
	9	✓ 899 5		1	✓ 900
	20	✓ 899 5		2	✓ 900
	1	✓ 899 9		3	✓ 899 8
	2	✓ 899 9		4	✓ 899 8
Sept 13	3	✓ 899 9		5	✓ 899 8
	4	✓ 899 9	9-27	6	✓ 900
	5	✓ 899 5		7	✓ 899 8
	6	✓ 897 5		8	✓ 899 8
	7	✓ 899 5		9	✓ 899 8
	8	✓ 899 9		60	✓ 899 9
	9	✓ 899 7	10-1	1	✓ REMELT
	30	✓ 899 9		2	✓ 900 1
	1	✓ 900 0		3	✓ 900
" 15	2	✓ 900 0		4	✓ 899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1907					
Octo	1	✓ 900	10-10	97	✓ 900
	6	✓ 899 9		98	✓ 900 1
4	7	✓ 900 1	10-12	99	✓ 900
	8	✓ 900		100	✓ 900 1
	9	✓ 900 1		1	✓ 900 1
	70	✓ 900 1		2	✓ 900 1
	1	✓ 900 1		3	✓ 900 1
	2	✓ 900		4	✓ 900 1
	3	✓ 899 9		5	✓ 900
	4	✓ 900 1		6	✓ 900 1
	5	✓ 900 1	10-14	7	✓ 900
	6	✓ 900 1		8	✓ 900
	7	✓ 900 1		9	✓ 900 1
	8	✓ 900 1		110	✓ 900 1
8	9	✓ 900	10-22	1	✓ 900
	80	✓ 900		2	✓ 899 8
	1	✓ 899 9		3	✓ 899 8
	2	✓ 899 9		4	✓ 900 1
	3	✓ 900		5	✓ 900
	4	✓ 900		6	✓ 899 9
	5	✓ 900		7	✓ 900 1
	6	✓ 900 1		8	✓ 900
	7	✓ 900 1		9	✓ 900 2
	8	✓ 900		120	✓ 900
	9	✓ 900 1		1	✓ REMELT.
	90	✓ 900 1		2	✓ 900
10-10	1	✓ 900		3	✓ 900
	2	✓ 900		4	✓ REMELT.
	3	✓ 900		5	✓ REMELT.
	4	✓ 900 1		6	✓ REMELT.
	5	✓ 900 1	10-24	7	✓ 900
	6	✓ 900		8	✓ 900

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1907.					
Octo 24	129	✓ 900 2	10/31	161	✓ 899 9
	130	✓ 900		2	✓ 899 8
	1	✓ 899 9		3	✓ 899 8
	2	✓ 900		4	✓ 900
	3	✓ 900 2		5	✓ 899 9
	4	✓ 900	11/4	6	✓ 900
	5	✓ 900		7	✓ 900 1
" 26	6	✓ 899 9		8	✓ 899 9
	7	✓ 899 9		9	✓ 899 9
	8	✓ 900 1	170		✓ 899 9
	9	✓ 899 9	1		✓ 899 8
	140	✓ 900	2		✓ 900
	1	✓ 900	11/6	3	✓ 899 9
	2	✓ 900		4	✓ 900 1
	3	✓ 899 9		5	✓ 900 1
	4	✓ 899 9		6	✓ 899 9
	5	✓ 899 9	11-8	7	✓ 900
28	6	✓ 900 +		8	✓ 900
	7	✓ 899 9		9	✓ 900
	8	✓ 900 +	180		✓ 900 1
	9	✓ 899 9	1		✓ 900
	150	✓ 899 9	2		✓ 899 9
	1	✓ 900	3		✓ 900
29.	152	✓ 900		4	✓ 899 9
	3	✓ 900	11/9	5	✓ 899 9
	4	✓ 900		6	✓ 899 9
	5	✓ 900		7	✓ 900
30	6	✓ 899 9	11-12	8	✓ 899 9
	7	✓ 900 0		9	✓ 899 8
	8	✓ 900 1	190		✓ 899 9
	9	✓ 900	1		✓ 899 9
	160	✓ 900 2	2		✓ 899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.		FINESS.	
11/19.	193	✓	8999	1-16	233	✓	8999	
	4	✓	8999		4	✓	8999	
	5	✓	8999		5	✓	900	
	6	✓	8999		6	✓	900	
	7	✓	8998		7	✓	900	
	8	✓	8997		8	✓	8999	
	9	✓	900	1-17	9	✓	8999	
	200	✓	9001		230	✓	900	
	1	✓	8999		1	✓	8999	
	2	✓	900		2	✓	900	
	3	✓	900		3	✓	900	
	4	✓	8999		4	✓	900	
11-21	5	✓	8999		5	✓	8997	agosto
	6	✓	8999	2-14	6	✓	9001	
	7	✓	900		7	✓	900	
	8	✓	9001		8	✓	900	
	9	✓	900		9	✓	900	
	210	✓	900		240	✓	900	
11-22	11	✓	9001	2-15	1	✓	8999	
	12	✓	8998		2	✓	900	
	13	✓	8999		3	✓	8999	
	14	✓	8999		4	✓	900	
	15	✓	8998		5	✓	8998	
	16	✓	8999	2-17	6	✓	8999	
Dec. 6.	17	✓	8999		7	✓	900	
	18	✓	8999		8	✓	8999	
	19	✓	8999		9	✓	900	
	220	✓	8998		250	✓	900	
	1	✓	8998	2-18	1	✓	900	
	2	✓	8999		2	✓	900	
					3	✓	8999	
					4	✓	8999	

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	NO. OF MELT.	FINESS.	DATE	NO. OF MELT.	FINESS.
1908					
July 18	250	899 9	2/27	286	899 9
" 19	6	900		7	900
	7	899 9		8	900
	8	900		9	900
	9	900		290	900
	260	899 9	2/28	1	899 9
20	1	899 9		2	899 9
	2	899 9		3	900
	3	900		4	900
	4	900		5	900
	5	900	2/29	6	900
21	6	899 9		7	900
	7	899 9		8	899 9
	8	899 9		9	900
	9	900		300	900
	270	900	3/2	1	899 9
24	1	899 9		2	900
	2	900		3	899 9
	3	899 9		4	900
	4	900		5	900
	5	899 9	3/26	6	899 9
25	6	900		7	900
	7	900		8	900
	8	899 9		9	899 9
	9	900		310	899 9
	280	900	3/27	1	899 9
26	1	899 9		2	900
	2	899 8		3	899 9
	3	899 9		4	900
	4	899 9		5	899 9
	5	899 8	3/30	6	900
				7	900

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1908					
March 30	318	✓ 899 9	4/4/08	350	✓ 899 9
	9	✓ remelt		1	✓ 900
	320	✓ 900		2	✓ 900
" "	1	✓ 900		3	✓ 900
	2	✓ 900		4	✓ 899 9
	3	✓ 900		5	✓ 900
	4	✓ 900	4/14	6	✓ 900
	5	✓ 900		7	✓ 900
April 1	6	✓ 900		8	✓ 899 9
	7	✓ 899 9		9	✓ 900
	8	✓ 899 9		360	✓ 899 9
	9	✓ 900	4/15	1	✓ 900
	330	✓ 899 9		2	✓ remelt
	1	✓ 899 9		3	✓ 900
	2	✓ 900		4	✓ 899 9
	3	✓ 900		5	✓ 899 9
	4	✓ 900	4/16	6	✓ 900
	5	✓ 900		7	✓ 900
4/2/08	6	✓ 900		8	✓ 900
	7	✓ 900		9	✓ 900
	8	✓ 900		370	✓ 900
	9	✓ 900	4/28	1	✓ 899 9
	340	✓ 900		2	✓ 899 9
	1	✓ 900		3	✓ 899 9
4/4/08	2	✓ 899 9		4	✓ 900
	3	✓ 900		5	✓ 899 9
	4	✓ 900 1	4/29	6	✓ 900 1
	5	✓ 900		7	✓ 900
	6	✓ 900		8	✓ 900 1
	7	✓ 900		9	✓ 899 9
	8	✓ 899 9		380	✓ 899 9
	9	✓ 900			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	NO. OF MELT.	FINENESS.	DATE	NO. OF MELT.	FINENESS.
1908					
April 30	381	900	5/26	413	900 1
	2	900		4	900
	3	900 1		5	900
	4	899 9	5/27	6	900
	5	900 1		7	900
May 1	6	900		8	900
	7	899 9		9	900
	8	900		420	899 9
	9	900	5/28	1	899 9
	390	899 9		2	900
	1	900		3	899 9
	2	900		4	899 9
	3	899 9		5	899 9
	4	899 9	6/11	6	900
	5	899 8		7	900
May 4	6	900		8	900
	7	899 9		9	900
	8	900		430	899 9
	9	899 9	6/12	1	900
	400	899 9		2	900
12	1	899 9		3	900
	2	899 9		4	899 9
	3	899 8		5	900
	4	899 9	6/13	6	900
	5	900		7	900
13	6	899 9		8	899 9
	7	899 9			
	8	899 8			
	9	899 9			
	410	899 8			
26	1	900			
	2	900			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1908 Aug 20	1	900 1	Aug 34	33	900
	2	900		34	900
	3	900 1		35	900
	4	900 1		36	899 9
	5	900 1		37	899 9
	6	900 1		38	899 9
23	7	900	38	39	900
	8	900 1		40	899 9
	9	900 1		41	900
	10	899 9		42	900
	11	899 9		43	899 9
	12	899 9	Sept 1	44	900
34	13	900		45	900
	14	900 1		46	900
	15	900		47	900
	16	900		48	899 9
	17	900		49	900 1
	18	900		50	900
	19	900		51	900 1
	20	900		52	899 9
25	21	900 1		53	900
	22	900 1		54	900
	23	900	12	55	899 9
	24	900		56	900
	25	900		57	899 9
	26	900 1		58	900
26	27	900	16	59	900
	28	900		60	900 1
	29	900		61	900
	30	900		62	900
	31	900		63	899 9
	32	899 9		64	900

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1908 Sept 16	65	900	Oct 1	97	900
	66	900		98	899 9
	67	900		99	899 9
	68	900 1		100	900
18	69	900		1	900
	70	900		2	900
	71	900	3	3	900
	72	900		4	900
	73	900 1		5	899 9
	74	900		6	900
	75	900 1	3	7	899 8
	76	900		8	899 8
22	77	899 9		9	899 8
	78	900		110	899 9
	79	900		1	900
	80	899 9		2	900
	81	899 9		3	900
	82	900		4	900
	83	900	6	5	900
	84	900		6	900
	85	899 9		7	900
	86	900		8	900
23	87	900	7	9	899 9
	88	900		120	899 9
	89	899 9		1	899 9
	90	900		2	900
29	91	899 9	8	3	900
	92	900 1		4	900
	93	900		5	900
	94	900		6	899 9
Oct 1	95	900	9	7	899 9
	96	900		8	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	No. OF MELT.	FINESS.	DATE	No. OF MELT.	FINESS.
1908			Nov		
Oct 9	129	900	16	161	899 9
	130	900		3	900
14	1	899 9		3	900
	2	899 9		4	899 9
	3	900		5	900
	4	900		6	900
	5	900	18	7	900
	6	900		3	900
	7	900		9	899 9
	8	900		170	899 9
16	9	900	24	1	900
	140	900	25	2	899 9
	1	900	"	3	899 9
	2	900	24	4	899 8
22	3	899 8	25	5	899 9
	4	899 9	"	6	899 9
	5	900	24	7	899 8
	6	900	24	8	899 9
Nov 10	7	899 9	25	9	900
	8	900		180	899 9
	9	899 8		1	900
	150	899 8		2	900
12	1	900	38	3	900
	2	899 9		4	900
	3	899 9		5	900
	4	899 9		6	900
13	5	899 9		7	900
	6	899 9		8	900
	7	899 9		9	900
	8	899 8		190	900
16	9	899 9	30	1	900
	160	899 9		2	900

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
Nov 30	193	900	12/11/68	320	899 9
	4	900		6	900
Dec. 14	5	899 9		7	900
	6	900		8	900
	7	900		9	900
	8	899 9		330	899 9
12/3	9	899 9		1	900
	200	900		2	900
	1	900	12/10/68	338	900
	2	900		333	900
12/4	3	900		4	900
	4	900		5	899 9
	5	900		6	899 9
	6	900		7	899 8
12/5	7	900		8	899 9
	8	900	12/16/68	9	899 9
	9	900		340	900
	210	899 9		1	899 9
	1	900		2	899 9
	2	900		3	900
	3	900		4	899 9
	4	900		5	900
12/8	5	900		6	900
	6	899 9	12/8/68	7	900
	7	899 9		8	899 9
	8	900		9	900
	9	900		350	900
	220	900		1	900
	1	899 9		2	899 9
	2	899 9		3	900
12/11/68	3	900		4	899 9
	4	900			

all
900 Remelt reported from assay

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1908					
Dec 19	355	900	1/23/09	291	900
	6	900		2	900
	7	900		3	900
	8	899 9		4	899 9
	9	900	1/25/09	5	899 9
	360	900		6	899 9
January 1909.				7	900
				8	899 9
Jan 16	367	899 9	2/10/09	9	899 9
	8	900		300	900
	9	899 9		1	899 9
	370	900		2	899 9
18	1	899 9	2/11/09	3	900
	2	900		4	900
	3	900		5	900
	4	900		6	900
19	5	900	2/13/09	7	900
	6	900		8	900
	7	899 9		9	900
	8	900		310	900
21	9	899 9	15	1	900
	080	899 9		2	900
	1	900		3	900
	2	900		4	900
	3	900	17	5	900
	4	900		6	900
	5	899 9		7	900
	6	900		8	900
22	7	899 9	18	9	899 9
	8	899 9		320	900
	9	900		1	899 9
	290	900		2	900

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	NO. OF MELT.	FINESS.	DATE	NO. OF MELT.	FINESS.
1909					
Feb 18	320	899 9	Feb	355	899 9
	4	900		6	899 9
	5	900		7	899 9
	6	900		8	900
20	7	900	18	9	899 8
	8	900		360	899 9
	9	899 9		1	899 9
	330	899 9		2	899 9
	1	900	19	3	900
	2	899 9		4	900
	3	900		5	899 9
	4	900		6	900
23	5	900	20	7	900
	6	900		8	900
	7	900		9	900
	8	900		370	900
24	9	900	23	1	900
	340	900		2	900
	1	900		3	900
	2	900		4	900
25	3	899 9		5	899 9
	4	899 9		6	900
	5	900		7	900
	6	900		8	900
26	7	900	25	9	899 9
	8	899 9		380	900
	9	899 9		1	899 9
	350	900		2	900
27	1	900		3	899 9
	2	900		4	900
	3	900		5	900
	4	900		6	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1909					
March 26	387	899 9	4/10/09	419	900
	8	900	17	420	900
	9	900		1	900
	390	900		2	900
27	1	900		3	900
	2	900		4	900
	3	900		5	900
	4	899 9	19	6	900
29	5	800		7	899 9
	6	899 9		8	900
	7	899 9	20	9	900
	8	900		430	900
31	9	900		1	900
	400	900	21	2	899 9
	1	900		3	899 9
	2	900		4	899 9
	3	900	22	5	899 9
	4	900		6	899 9
	5	900		7	899 8
April 1	6	900	23	8	899 9
	7	900		9	900
	8	900		440	900
	9	900	24	1	899 9
	410	900		2	900
13	1	900		3	899 9
	2	900	26	4	899 9
	3	899 9		5	899 9
14	4	899 9	May	6	899 9
	5	899 9	11	7	899 9
	6	900		8	899 9
15	7	900		9	899 9
	8	900			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	No. OF MELT.	FINESS.	DATE	No. OF MELT.	FINESS.
1909 May 12	450	900	6/4/09	482	900
	1	900	48/09	3	900
	2	8999		4	8999
13	3	8999		5	900
	4	900		6	900
	5	8999	9	7	8999
14	6	900		8	8999
	7	900		9	8999
	8	8999			8999
15	9	8999	10/09	1	900
	460	8999		2	900
	1	900		3	900
22	2	8999		4	8999
	3	8999	11	5	8999
	4	8999		6	8998
24	5	900		7	8998
	6	8999		8	8998
25	7	900	16	9	8999
	8	8999			8998
	9	8999		1	8999
26	470	900		2	8998
	1	8999	17	3	8999
27	2	8999		4	8998
	3	8999		5	8999
	4	8999		6	8998
June 3	5	8999	21	7	8998
	6	900		8	8999
	7	900	22	9	8999
	8	900			
	9	900			
4	480	8999			
	1	8999			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
Jan 6. 1910.	1	900	1/25/10	33	899 9
	2	900 1		34	900
	3	900		35	900 2
	4	900		36	900
7	5	899 9	28	37	900
	6	900		38	900
	7	900		39	900
	8	900		40	900
8	9	900		41	899 9
	10	900		42	899 9
12	11	900	29	43	900
	12	899 9	Feb 2/10	44	900
	13	900		45	899 9
	14	899 9		46	899 9
14	15	899 9		47	900
	16	899 9		48	900
	17	899 9		49	900
	18	899 8		50	900
17	19	900	7	51	900
	20	900 1		52	900
	21	900		53	900
	22	900		54	900
21	23	900		55	900
	24	900	10	56	899 9
	25	900		57	900
	26	900		58	900
	27	900 1		59	899 9
	28	900		60	900
22	29	899 9		61	900
	30	900		62	899 9
	31	900	14	63	900
	32	900		64	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.	
1910						
Feb 14	65	8999	Feb 5	97	900	
	66	8999		98	8998	
	67	8999		99	900	
	68	900		100	8999	
	69	8999		101	900	
	70	8999		102	900	
16	71	8999	8	103	900	0007 ag
	72	8999		04	900	
	73	8999		05	900	
	74	8999		06	900	
18	75	8999	12	7	8999	
	76	8999		8	8999	
	77	900		9	9001	
	78	900		110	9001	
23	79	8999		1	900	
	80	900		2	8999	
	81	8999	16	3	8999	
	82	8998		4	8998	
	83	8999		5	8999	
	84	8999		6	8999	
26	85	8999		7	900	
	86	8999		8	8999	
	87	900		9	900	
	88	900		120	900	
	89	8999	18	1	900	
	90	900		2	8999	
Feb 2	91	900		3	900	
	92	8999		4	900	
	93	900	22	5	900	
	94	900		6	900	
	95	8999		7	8999	
	96	8999		8	900	

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1910 Mch 23	149	900	April 12	161	900
	180	899 8		162	900
	181	900		163	900
	182	900		164	899 9
24	133	900		165	900
	134	899 9		166	899 9
	135	900	15	167	900
	136	899 9		168	900
29	137	899 9		169	900
	138	899 9		170	900
	139	900 1	19	171	900
	140	900		172	899 9
30	141	899 9		173	900
	142	899 9		174	899 9
	143	900		175	899 9
	144	900		176	899 9
April 2	145	900		177	899 9
	146	900		178	900
	147	900	22	179	900
	148	900		180	900
5	149	899 9		181	899 8
	150	900		182	899 9
	151	900	23	183	900
	152	900		184	899 9
8	153	900		185	899 9
	154	899 9		186	899 9
	155	899 9	26	187	900
	156	899 9		188	899 9
	157	899 9		189	900
	158	900		190	900
	159	900	27	191	899 9
	160	900	19	192	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1910					
April 29	193	899 9		225	900
	194	899 9		226	899 9
	195	899 9		227	899 9
	196	899 9	May	228	899 9
May 2	197	899 9	20	229	900
	198	899 9		230	899 9
6	199	900		231	900
	200	900		232	899 9
	201	899 9	24	233	899 9
	202	899 9		234	900
	203	899 9		235	900
	204	900		236	899 9
	205	900		237	900
	206	899 9		238	900
7	207	899 9	26	239	899 9
	208	900		240	899 9
	209	900		241	899 9
	210	900		242	899 9
10	211	899 9	28	243	900
	212	900		244	900
	213	900		245	900
	214	900	June 1	246	899 9
14	215	900	1	247	900
	216	Amult		248	900
	217	900		249	900
	218	900		250	899 9
	219	899 9	3	251	900
	220	900		252	900
18	221	900 1		253	899 9
	222	900		254	899 8
	223	899 9	6	255	899 9
	224	899 9		256	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1910			June		
June 6	257	899 9	23	289	900
	258	899 9		290	900
10	259	899 8		291	899 9
	260	899 9	25	292	900
	261	900		293	900
	262	899 9			
	263	900			
	264	900			
	265	899 9			
	266	899 9			
14	267	899 9			
	268	900			
16	269	900			
	270	899 9			
17	271	899 9			
	272	899 9			
	273	899 9			
	274	900			
18	275	900			
	276	899 9			
	277	900			
	278	900			
22	279	900			
	280	900			
	281	899 9			
	282	899 9			
	283	900			
	284	900			
23	285	900			
	286	900			
	287	900			
	288	900			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1910 Aug 29	1	899 9	Sept 22	32	899 9
	2	899 9		33	899 9
	3	899 5		34	899 8
	4	899 9		35	899 8
	5	899 9	9/26	36	899 8
	6	899 8	"	37	899 8
	7	899 9	7-27	38	899 9
	8	899 9		39	899 9
	9	899 9		40	900 0
	10	899 8		41	899 9
	11	899 8		42	899 8
	12	899 9	7-29	43	899 8
	13	899 9		44	899 9
	14	899 8	7-29	45	899 9
	15	899 9		46	899 8
	16	900 0	10-4	47	899 9
	17	900 0	Oct 6	48	899 9
	18	899 9	4	49	900
	19	900 0		50	900
	20	899 9		51	900
	21	899 8		52	900
	22	899 9	5	53	900
Sept 17	23	899 9		54	900
	24	899 9		55	899 9
" 19	25	899 9	7	56	900
	26	899 9		57	900 1
	27	899 8		58	900
	28	900 0		59	900
	29	899 9	10	60	900
" 21	30	899 9		61	900
	31	899 9		62	900
				63	900

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1910					
Oct 13	64	8999	Oct 29	96	900
	65	900		97	900
	66	900	31	98	900
	67	8999		99	900
	68	900		100	900
	69	900		101	900
14	70	8999	Dec 17	102	8999
	71	8999		103	900
15	72	900	20	104	8999
	73	900		105	8999
18	74	900	22	106	900
	75	900		107	8999
19	76	900		108	900
	77	900		109	900
20	78	900	22	110	8999
	79	900		111	900
	80	900		112	900
	81	900		113	900
21	82	900		114	900
	83	900		115	900
22	84	900		116	8999
	85	900		117	900
25	86	900	24	118	900
	87	900		119	900
	88	900		120	900
	89	900		121	900
26	90	900	30	122	900
	91	900		123	900
27	92	900		124	8999
	93	900		125	900
28	94	900			
	95	900			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	NO. OF MELT.	FINESS.	DATE	NO. OF MELT.	FINESS.
1911			January		
Jan 10	126	900 0	23	158	900
	127	900 0		159	900
	128	899 9		160	900
Jan 11	129	899 9	24	161	899 9
	130	900 0		162	899 9
	131	900 0		163	899 9
Jan 13	132	900 0	26	164	900
	133	900 0		165	899 8
	134	899 9		166	899 9
	135	900 0	27	167	899 9
	136	900 0		168	900
	137	900 0		169	900
Jan 16	138	900 0	28	170	900
	139	899 9		171	900
	140	900 0		172	900
	141	899 9	30	173	900
	142	899 9		174	900
	143	899 9		175	900
Jan 17	144	900 0	31	176	900
	145	900 0		177	900
18	146	899 9	February	178	900
	147	899 9		179	899 9
	148	900		180	900
19	149	900		181	899 9
	150	900	2	2	899 9
	151	899 9		3	899 9
Jan 21	152	899 9		4	899 9
	153	899 9	11	5	900 1
	154	900 0		6	899 9
	155	900 0		7	899 9
	156	899 9		8	900
	157	900 0		9	900

ASSAYER'S REGISTER OF GOLD INGOTS.

2-2229

DATE.	No. of MELT.	FINENESS.	DATE.	No. of MELT.	FINENESS.
1911					
Feb'y 11	190	900	2/27/11	222	900
13	191	899 9		223	900
	192	899 9	27	224	900
	193	899 9		5	899 9
14	194	900		6	900
	195	900	28	7	900
	196	900		8	899 9
15	197	899 9		9	900
	198	900	ncp	320	899 9
	199	900		1	899 9
16	200	900		2	900
	201	899 9	7	3	900
	202	900		4	900
18	203	900		5	900
	204	900	8	6	899 9
	205	900		7	900
20	206	900		8	900
	207	899 9	9	9	899 8
	208	900		240	899 9
21	209	900		1	899 8
	210	900	13	2	899 8
	211	900		3	899 8
23	212	899 9		4	899 9
	213	899 9		5	900
	214	899 9		6	899 9
	215	899 9		7	899 9
	216	899 9		8	899 9
	217	899 9		9	899 9
25	218	900		200	899 9
	219	900	14	1	899 8
	220	900		2	899 8
	221	900		3	899 8

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1911 Mar 15	254	899 9	4/14	285	900
	255	899 9		286	899 9
	256	899 9		287	900
16	357	899 9		288	900
	258	899 9		289	899 9
	259	899 9		290	900
17	260	899 9	4/15	291	900
	261	899 8		292	900
	262	899 9		293	900
18	263	899 9		294	899 9
	264	899 9		295	899 9
	265	899 9	4/17	296	900
26	266	899 9		297	900
	267	899 9		298	900
	268	899 9		299	899 9
27	269	900		300	900
	270	899 9		301	899 9
	271	899 9	4/19	2	899 9
April 3	272	900		3	900
	273	899 9		4	900
	274	899 9		5	900
	275	899 9		6	900
	276	899 9		7	900
8	277	900	4/22	8	900
	278	900		9	899 9
10	279	900		310	899 8
8	280	900	3	1	900
"	281	900		2	900
10	282	906		3	900
	283	900		4	900
	284	900		5	900
				6	910

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1911					
May 5	317	8999			
	318	8999			
	319	8999			
6	320	900			
	321	900			
	322	900			
9	323	900			
	324	900			
	325	900			
11	326	900			
	327	900			
12	328	900			
13	329	8999			

ASSAYER'S REGISTER OF GOLD INGOTS.

9-2020

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1913					
Jan 13	1	900 0	1-18	33	Re-melt
	2	899 9		4	899 9 ✓
	3	900 0		5	899 9 ✓
	4	900 0		6	899 8 ✓
Jan 14	5	900 0		7	899 9 ✓
	6	899 9		8	899 9 ✓
	7	900 0		9	899 9 ✓
	8	900 0		40	899 8 ✓
	9	899 9		1	899 9 ✓
	10	899 9		2	900 0 ✓
	11	900 0		3	900 0 ✓
	12	899 9	20	4	899 9 ✓
	13	899 9		5	900 ✓
	14	899 9		6	900 1 ✓
	15	900		7	899 9 ✓
	16	899 9	23	8	900 0 ✓
Jan 15	17	900 0		9	900 0 ✓
	18	900 0		50	900 1 ✓
	19	899 9		1	900 0 ✓
	20	899 9		2	900 0 ✓
	1	899 9		3	899 9 ✓
	2	899 9		4	899 9 ✓
	3	900 0		5	900 0 ✓
	4	899 9	24	6	900 1 ✓
	5	900 0		7	900 0 ✓
	6	900 0		8	900 0 ✓
	7	899 9		9	899 9 ✓
	8	900 1		60	900 1 ✓
	9	900 0		1	900 0 ✓
	20	899 9		2	900 0 ✓
	1	899 9		3	899 9 ✓
	2	899 9	27	4	899 9 ✓

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1913					
Jan 27	65	8999	2-4	97	8999
	6	9000		98	9000
	7	8999		9	8999
	8	8999	2-5	100	8999
	9	9000		1	9000
	70	8999		2	9000
	1	8999		3	9000
" 28	2	9000	12-6	104	8999
	3	9000		5	8999
	4	8999		16	9000
	5	8999		7	8999
" 29	76	9001	12-7	8	9000
	7	9000		9	8999
	8	9001		110	8999
	9	9000		1	8999
" 31	80	9000	2-10	2	8999
	1	8999		3	8999
	2	8999		4	8999
	3	9000		5	8999
Feb 1	84	8999		6	8999
	5	8999		7	8999
	6	9000		8	8999
	7	8999		9	8999
	8	8999	2-14	120	8999
	9	8999		1	8999
	90	8998		2	8999
	1	9000		3	8999
Feb 4	2	8999		4	8998
	3	8999		5	8999
	4	9001		6	8998
	5	9000		7	9000
	6	8999	June 7	8	8999

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.		FINESS.
1913				1914			
June 7	129		899 8	4/11	24		899 9 ✓
	130	Remelt		4/13	25		900 ✓
	1		899 7		26		899 7 ✓
	2		899 5		27		899 9 ✓
	3		899 7		28		899 8 ✓
" "	4		899 5	4/14	29		900 ✓
				"	30		899 8 ✓
1913				"	31		899 9 ✓
Dec 2	1		900 0	"	32		899 8 ✓
	2		899 8	4/15	33		899 9 ✓
	3		899 8	"	34		899 7 ✓
	4		900 0	"	35		899 8 ✓
	5	Remelt		"	36		899 7 ✓
	6	"		16	37		899 9 ✓
Dec 31	7		900 1	"	38		899 9 ✓
"	8		900 1	"	39		899 8 ✓
"	9		900	"	40		900 ✓
"	10		899 9	17	41		899 9 ✓
"	11		900 1	"	42		900 ✓
"	12		900	"	43		900 ✓
"	13	M-R	900	"	44		899 9 ✓
1914	13	Remelt		20	45		900 1 ✓
April 10	14	Remelt		"	46		899 8 ✓
"	15		899 8	"	47		899 8 ✓
"	16	Remelt		"	48		899 9 ✓
"	17		899 7	"	49		899 9 ✓
"	18	Remelt		"	50		899 9 ✓
"	19		899 8	"	51		899 9 ✓
"	20		899 8	"	52		900 0 ✓
"	21	Remelt		21	53		900 2 ✓
"	22		899 7	"	54		900 ✓
"	23		900	"	55		900 ✓

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	No. OF MELT.	FINESS.	DATE	No. OF MELT.	FINESS.
1914			1914		
April 21	56	900	58	88	8999 ✓
22	57	8999	74	89	900 ✓
"	58	900	"	90	8999 ✓
"	59	8997	"	91	8998 ✓
"	60	8998	"	92	8998 ✓
23	61	8999	15	93	8998 ✓
"	62	900	16	94	8999 ✓
"	63	8999	"	95	8999 ✓
"	64	8999	"	96	9000 ✓
24	65	8999	19	97	8999 ✓
"	66	8998	"	98	8998 ✓
"	67	8997	"	99	8999 ✓
"	68	8998	22	100	8998 ✓
25	69	8998	"	101	8998 ✓
"	70	8999	29	102	8998 ✓
"	71	8999			
"	72	8999			
27	73	8998 ✓			
"	74	9000 ✓			
"	75	8999 ✓			
"	76	8998 ✓			
28	77	9001 ✓			
"	78	9000 ✓			
"	79	8999 ✓			
"	80	8998 ✓			
29	81	8999 ✓			
"	82	8998 ✓			
"	83	8998 ✓			
"	84	8998 ✓			
May 8	85	9000 ✓			
"	86	9000 ✓			
"	87	8999 ✓			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1914 Oct 14	1	900			
" "	2	900 1			
" "	3	900			
" "	4	900			
" "	5	900 1			
" "	6	899 9			
" 2	7	899 9			
" "	8	900			
" "	9	900			
" "	10	900			
" "	11	899 9			
" "	12	900			
3	13	900			
" "	14	899 9			
" "	15	899 9			
" "	16	899 9			
" "	17	899 9			
" "	18	899 9			
5	19	900			
" "	20	900			
" "	21	900 1			
" "	22	900			
" "	23	899 9			
" "	24	899 9			
6	25	899 9			
" "	26	900			
" "	27	900			
" "	28	900			
7	29	899 9			
" "	30	900 0			
" "	31	899 9			
" "	32	900 0			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1914					
Oct. 7	33	8999	119	65	900
" 8	34	8999		6	900
	35	8999		7	8999
	36	8999		8	900
	37	8999	20	69	8999
	38	8999		70	900
14	39	8999		1	900
	40	8999		2	900
	1	8998		3	900
	2	8999		4	8999
	3	8999	21	5	900
	4	900		6	900
15	5	900		7	8999
14	6	900		8	8999
14	7	900		9	8999
15	8	900		80	900
"	9	900	22	81	900
"	50	900.1		2	900
16	51	900		3	8999
	2	900		4	8999
	3	900		5	900
	4	900		6	8999
	5	900	23	7	900
	6	8999		8	8999
17	7	900		9	900
	8	900		90	900
	9	900		1	8999
	60	8999		2	900
	1	900	24	3	8999
	2	900		4	8999
19	3	900		5	900
	4	900		6	8999

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1914			1914		
Oct 24	99	899 8	19	129	899 9 ✓
	8	900		130	899 9 ✓
26	99	900		1	899 9 ✓
	100	899 9		2	899 9 ✓
	1	900	Nov 21	133	899 8 ✓
	2	900		4	899 8 ✓
	3	899 8		5	899 9 ✓
	4	900		6	899 9 ✓
27	105	900 1		7	900 0 ✓
	6	900		8	900 0 ✓
	7	900	Dec 1	139	899 8 ✓
	8	900		140	900 0 ✓
28	109	899 8		1	899 9 ✓
	110	900 0		2	899 9 ✓
	11	900 0		3	899 9 ✓
	12	900 0		4	899 9 ✓
	13	899 9	12/4	145	899 8 ✓
	14	900 1		6	899 8 ✓
Nov 17	115	900 0	12/5	7	900 0 ✓
	6	899 8		8	900 0 ✓
	7	899 9	12/7	9	899 9 ✓
	8	900 0		150	899 9 ✓
	9	900 0	12/5	1	899 9 ✓
	120	900 0		2	899 9 ✓
18	1	899 9	1/16	3	900 ✓
	2	899 9		4	899 9 ✓
	3	899 9	1/17	5	899 8 ✓
	4	899 9		6	899 7 ✓
	5	899 9		7	899 9 ✓
	6	899 9	1/35	8	899 9 ✓
19	127	900	"	9	899 8 ✓
	8	900			

ASSAYER'S REGISTER OF GOLD INGOTS.

1919 DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.		FINESS.
Jan'y	10	1	899 8	1919 Oct 8	17	Perm	916 8
"	"	2	899 9		18	"	916 9
"	"	3	899 8		19	"	916 7
"	"	4	899 8		20	"	916 6
"	"	5	899 8	9	21	"	916 7
"	"	6	899 7		22	"	916 7
"	11	7	899 9		23	"	916 8
"	11	8	899 8	10	24	"	916 7
"	11	9	899 7		25	"	916 6
"	11	10	900 0		26	"	916 8
"	11	11	899 7		27	"	916 6
"	11	12	899 9		7		
"	13	13	899 9				
"	"	14	900 0				
"	"	15	900 0				
1919 July	11	1	916 7				
		2	916 7				
		3	916 7				
		4	916 6				
		5	916 6				
		6	916 7				
14		7	916 7				
		8	916 6				
		9	916 6				
16		10	916 7				
		11	916 7				
17		12	916 5				
		13	916 6				
18		14	916 5				
		15	916 5				
		16	916 6				

Peruvian Pound Blanks

ASSAYER'S REGISTER OF GOLD INGOTS.

ASSAYER'S REGISTER OF GOLD INGOTS.

[illegible]

ASSAYER'S REGISTER OF GOLD INGOTS.

2-2220

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.
1923				1923			
Apr. 14	1		8999	May 3	33		8999
	2		8998		34		8999
Apr. 16	3		8998	May 4	35		8999
	4		8998		36		9000
Apr. 17	5		9000	May 5	37		9000
	6		8999		38		9001
Apr. 18	7		9001	May 7	39		9000
	8		9000		40		8998
Apr. 19	9		8999		41		8999
	10		8999	May 8	42		9000
Apr. 20	11		8999		43		8999
	12		8999	May 9	44		8999
Apr. 21	13		8999		45		9000
	14		8999	May 10	46		8999
Apr. 23	15		9000		47		9000
	16		9000	May 11	48		8999
Apr. 24	17		8999		49		8999
	18		8999	May 12	50		8998
Apr. 25	19		8998		51		8998
	20		8998		52		8999
Apr. 26	21		8999	May 14	53		8998
	22		9000		54		8998
Apr. 27	23		8999		55		9000
	24		8998	May 15	56		8999
Apr. 28	25		8998		57		8999
	26		8999		58		8999
Apr. 30	27		8999	May 16	59		9000
	28		8999		60		9000
May 1	29		8999		61		8999
	30		8998	May 17	62		8999
May 2	31		8998		63		8999
	32	R.M.	8998		64		8999

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1923			1923		
May 18.	65	8998		97	8998.
	66	8998	June 1	98	8999
	67	8998		99	8998
May 19	68	8999		100	8997
	69	8999	June 2	101	8998
	70	8998		102	8997
May 21	71	8999		103	8998
	72	8999	June 4	104	8997
	73	8999		105	8997
May 22	74	8998		106	8997
	75	8999	June 5	107	8997
	76	9000		108	8997
May 23.	77	8998		109	8998
	78	8999		110	8997
	79	8999		111	8998
May 24	80	8998	June 6	112	8997
	81	8999		113	8997
	82	8999		114	8998
May 25	83	8998		115	8999
	84	8998		116	8998
	85	8999	June 7	117	8999
May 26	86	8998		118	8997
	87	8999		119	8998
May 28	88	8997		120	8997
	89	8999		121	8999
	90	8998	June 8	122	8997
	91	8997		123	8998
May 29	92	8997		124	8997
	93	8998		125	8997
	94	8997		126	8997
May 31	95	8999	June 9	127	8999
	96	9000		128	8998

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.	No. of samples
1923			1923	Aug 2-23		
	129	8998		1	900 -	5
	130	8998		2	900 -	6
	131	8997		3	900 -	7
June 11	132	8998		4	7/3/23 899 8	8
	133	8998		5	899 9	"
	134	8997		6	899 9	"
	135	8997		7	899 8	"
	136	8998		8	8/9/23 899 8	"
June 26	137	8997		9	899 8	"
	138	8998		10	8/11/23 899 7	"
	139	8997		11	" 899 8	"
	140	8997		12	8/13/23 899 9	"
	141	8998		13	899 8	"
	142	8998		14	8/14/23 899 8	"
	143	8997		15	" 899 9	"
	144	8997		16	8/15/23 899 9	"
	145			17	899 8	"
	146			18	8/17/23 899 9	"
	147			19	" 899 9	"
	148			20	" 899 8	"
	149			21	899 8	"
	150			22	8/20/23 899 8	"
	151			23	" 899 8	"
	152			24	" 899 8	"
	153			25	" 899 7	"
	154			26	8/31/23 899 8	"
	155			27	" 899 8	"
	156			28	8/22/23 899 8	"
	157			29	" 899 9	"
	158			30	" 899 9	"
	159			31	899 9	"
	160			32	8/23/23 899 9	"

ASSAYER'S REGISTER OF GOLD INGOTS.

9-2025

DATE.	No. OF MELT.		FINENESS.	DATE.	No. OF MELT.		FINENESS.
1923				1923			
8/25/23	33	<i>5 samples in all ingot mels</i>	899 9	9/12/23	65	<i>5 samples in all ingot mels</i>	899 8
"	34		899 9	9/13/23	66		899 7
"	35		899 8	"	67		899 7
8/27/23	36		899 9	"	68		899 8
"	37		899 8	9/14/23	69		899 9
8/28/23	38		899 8	"	70		899 7
"	39		899 8	"	71		899 8
8/29/23	40		899 9	9/17/23	72		899 8
"	41		899 8	"	73		899 8
8/30/23	42		899 8	"	74		899 8
"	43		899 8	"	75		899 9
8/31/23	44		899 9	"	76		899 8
"	45		899 8	9/18/23	77		899 8
9/4/23	46		899 8	"	78		899 7
"	47		899 9	"	79		899 8
"	48		899 8	9/19/23	80		899 8
"	49		899 7	"	81		899 8
9/5/23	50		899 8	"	82		899 8
"	51		899 9	9/20/23	83		899 8
9/6/23	52		899 7	"	84		899 8
"	53		899 8	"	85		899 8
9/7/23	54		899 7	9/21/23	86		899 8
"	55		899 8	"	87		899 8
9/8/23	56		899 8	"	88		899 8
"	57		899 8	9/22/23	89		899 8
"	58		899 7	"	90		899 8
9/10/23	59		899 9	"	91		899 7
9/11/23	60		899 8	9/24/23	92		899 8
"	61		899 8	"	93		899 7
"	62		899 8	"	94		899 8
9/12/23	63		899 9	9/26/23	95		899 8
"	64		899 8	"	96		899 8

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE. 1923	No. OF MELT.	FINENESS.	DATE. 1923	No. OF MELT.	FINENESS.
9/26/23	97	899 8	10/7/23	129	899 8
"	98	899 7	"	130	899 8
"	99	899 8	10/10/23	131	899 7
"	100	899 8	"	132	899 7
9/27/23	101	899 8	"	133	899 8
"	102	899 7	10/11/23	134	899 8
"	103	899 8	"	135	899 8
9/28/23	104	899 8	"	136	899 8
"	105	899 8	10/12/23	137	899 9
"	106	899 8	"	138	899 7
9/29/23	107	899 7	"	139	899 8
"	108	899 8	"	140	899 8
"	109	899 8	"	141	899 8
10/2/23	110	899 8	"	142	899 9
"	111	899 8	10/3/23	143	899 9
"	112	899 8	"	144	899 8
10/3/23	113	899 9	"	145	899 8
"	114	899 8	10/5/23	146	899 7
"	115	899 8	"	147	899 8
10/5/23	116	899 8	"	148	899 9
"	117	899 8	10/14/23	149	899 8
"	118	899 8	"	150	899 7
"	119	899 8	"	151	899 8
"	120	899 7	"	152	899 7
"	121	899 9	"	153	899 7
10/5/23	122	899 8	"	154	899 8
"	123	899 8	10/18/23	155	899 8
"	124	899 7	"	156	899 8
10/6/23	125	899 9	"	157	899 7
"	126	899 9	10/19/23	158	899 8
"	127	899 8	"	159	899 8
10/7/23	128	899 8	"	160	899 8

5 francs plus in all ingot made

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.		FINENESS.	DATE.	NO. OF MELT.		FINENESS.
1923				1924			
12/21	288		899 8	1/7/24	320		899 7
	289		899 8	"	321		899 8
	290		899 8	"	322		899 7
12/22	291		899 8	"	323		899 8
	292		899 7	"	324		899 8
	293		899 8	"	325		899 8
12/26	294		899 8	1/8/24	326		899 8
	295		899 9	"	327		899 8
	296		899 8	"	328		899 8
12/27	297		899 8	1/10/24	329		899 8
	298		899 8	"	330		899 8
	299		899 7	"	331		899 8
12/28	300		899 8	1/10/24	332		899 8
	301		899 7	"	333		899 8
	302		899 8	"	334		899 8
12/29	303		899 7	1/12/24	335		899 8
	304		899 7	"	336		899 8
	305		899 8	"	337		899 8
12/31	306		899 8	1/14/24	338		899 8
	307		899 7	"	339		899 8
	308		899 8	"	340		899 8
1/3/24	309		899 8	1/15/24	341		899 7
"	310		899 8	"	342		899 8
"	311		899 8	"	343		899 8
"	312		899 8	1/16/24	344		899 8
"	313		899 8	"	345		899 8
"	314		899 8	"	346		899 8
1/4/24	315		899 8	1/17/24	347		899 8
"	316		899 8	"	348		899 8
"	317		899 8	"	349		899 8
"	318		899 8	1/18/24	350		899 8
"	319		899 8	"	351		899 7

5 bars of 100 gms each

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1924			1924		
1/18/24	352	899 8	1/21/24	384	899 7
1/19/24	353	899 8		385	899 7
"	354	899 8	2/1/24	386	899 8
	355	899 8	"	387	899 8
1/21/24	356	899 7	"	388	899 8
"	357	899 7	2/2/24	389	899 8
"	358	899 8	"	390	899 8
1/22/24	359	899 8	"	391	899 8
"	360	899 8	2/4/24	392	899 8
	361	899 7	"	393	899 7
1/23/24	362	899 8	"	394	899 8
"	363	899 8	2/4/24	395	899 8
"	364	899 7	"	396	899 8
1/24/24	365	899 8	"	397	899 8
"	366	899 8	2/4/24	398	899 8
	367	899 8	"	399	899 8
1/25/24	368	899 8	"	400	899 8
"	369	899 8	2/7/24	401	899 8
"	370	899 8	"	402	899 8
1/26/24	371	899 8	"	403	899 8
"	372	899 8	2/8/24	404	899 8
	373	899 8	"	405	899 8
1/28/24	374	899 8	"	406	899 8
"	375	899 7	2/9/24	407	899 8
"	376	899 7	"	408	899 8
1/29/24	377	899 7	"	409	899 8
"	378	899 8	2/11/24	410	899 8
	379	899 8	"	411	899 8
1/30/24	380	899 8	"	412	900 0
"	381	899 8	2/12/24	413	899 8
"	382	899 8	"	414	899 8
1/31/24	383	899 8	"	415	899 8

5 bars plus in all largest melt

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1924			1924		
2/13/24	416	899 7	2/25/24	448	899 8
"	417	899 8	"	449	899 9
"	418	899 8	"	450	900 0
2/14/24	419	899 9	2/26/24	451	899 9
"	420	899 9	"	452	899 9
"	421	899 9	"	453	899 8
2/15/24	422	900 0	2/27/24	454	899 7
"	423	900 0	"	455	899 9
"	424	899 9	"	456	899 8
2/16/24	425	900 0	"	457	899 9
"	426	900 0	"	458	899 8
"	427	900 0	2/28/24	459	899 9
2/18/24	428	899 9	"	460	900 0
"	429	899 9	"	461	900 0
"	430	899 8	"	462	899 9
2/19/24	431	899 9	2/29/24	463	900 0
"	432	899 9	"	464	899 9
"	433	899 9	"	465	899 9
"	434	899 9	"	466	900 0
2/20/24	435	899 8	3/3/24	467	900 0
"	436	899 8	"	468	899 9
"	437	899 9	"	469	899 8
"	438	899 8	"	470	899 9
2/21/24	439	899 9	3/14/24	471	800 0
"	440	899 8	"	472	900 0
"	441	899 9	"	473	899 9
"	442	899 9	"	474	899 9
2/23/24	443	899 8	"	475	900 0
"	444	899 8	"	476	900 0
"	445	899 9	"	477	899 9
"	446	899 9	"	478	900 0
2/25/24	447	899 7	3/6/24	479	899 9

5 samples in all high marks

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	No. OF MELT.	FINESS.	DATE.	No. OF MELT.	FINESS.
1924			1924		
3/6/24	480	899 9	3/15/24	512	899 9
"	481	900 0		513	899 9
"	482	899 9		514	899 9
"	483	899 8	3/17/24	515	899 8
"	484	899 9	"	516	899 8
"	485	899 8	"	517	899 8
"	486	899 9	"	518	899 8
3/7/24	487	899 9	3/18/24	519	900 0
"	488	899 9	"	520	899 8
"	489	899 9	"	521	899 9
"	490	899 9	"	522	899 9
3/8/24	491	899 9	"	523	899 9
"	492	899 9	"	524	899 9
"	493	899 9	"	525	899 9
"	494	899 9	"	526	899 8
3/10/24	495	899 9	3/19/24	527	899 8
"	496	899 9	"	528	899 8
"	497	899 8	"	529	900 0
"	498	899 8	"	530	900 0
3/11/24	499	899 9	3/20/24	531	900 0
"	500	899 9	"	532	900 0
"	501	899 9	"	533	900 9
"	502	899 8	"	534	899 9
3/12/24	503	899 9	"	535	900 0
"	504	899 9	"	536	899 9
"	505	899 8	"	537	899 9
"	506	899 8	"	538	899 8
3/13/24	507	899 8	3/24/24	539	900 0
"	508	899 8	"	540	899 9
"	509	899 8	"	541	899 9
"	510	899 8	"	542	899 8
3/15/24	511	899 8	"	543	899 9

Sample in all ingots mtd

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1924			1924		
3/21/24	544	899 9	4/3/24	576	899 8
3/25/24	545	899 8	"	577	899 9
"	546	899 9	"	578	899 9
"	547	900 0	4/4/24	579	899 8
"	548	899 9	"	580	899 8
3/27/24	549	899 8	"	581	899 8
"	550	899 9	"	582	899 9
"	551	899 9	4/5/24	583	900 0
"	552	899 9	"	584	899 9
"	553	899 9	"	585	899 8
"	554	899 8	"	586	899 8
3/28/24	555	899 8	4/7/24	587	900 0
"	556	899 9	"	588	899 9
"	557	899 9	"	589	899 9
"	558	899 8	"	590	899 9
"	559	899 8	"	591	899 8
"	560	899 9	"	592	899 9
"	561	899 9	"	593	899 8
"	562	899 9	"	594	899 8
3/31/24	563	899 9	4/10/24	595	899 8
"	564	899 8	"	596	899 9
"	565	899 8	"	597	899 7
"	566	899 9	"	598	899 8
4/1/24	567	899 8	"	599	899 9
"	568	899 8	"	600	899 9
"	569	899 8	"	601	899 8
"	570	899 9	"	602	899 8
4/2/24	571	899 9	"	603	899 9
"	572	899 9	"	604	899 9
"	573	899 9	"	605	899 9
"	574	900 0	"	606	899 8
4/3/24	575	900 0	4/11/24	607	899 8

5 samples in all "ingot melts"

ASSAYER'S REGISTER OF GOLD INGOTS.

5 samples to each "melt"

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1924			1924		
4/11/24	608	899 9	4/11/24	640	899 8
"	609	899 9	"	641	899 9
"	610	899 9	"	642	899 9
4/12/24	611	899 9	4/12/24	643	899 9
"	612	899 9	"	644	899 9
"	613	900 0	"	645	899 8
"	614	899 9	"	646	899 9
4/14/24	615	899 8	4/14/24	647	899 8
"	616	899 7	"	648	899 8
"	617	899 8	"	649	899 8
"	618	899 8	"	650	899 9
4/16/24	619	899 9	4/16/24	651	899 9
"	620	899 9	"	652	899 8
"	621	899 9	"	653	899 9
"	622	899 8	4/17/24	654	899 8
4/17/24	623	899 9	4/17/24	655	899 7
"	624	899 9	"	656	899 8
"	625	899 9	"	657	899 7
"	626	899 9	"	658	900 0
4/18/24	627	899 9	4/18/24	659	899 8
"	628	899 9	"	660	899 9
"	629	899 8	4/19/24	661	899 9
"	630	899 7	"	662	900 0
4/19/24	631	899 9	"	663	899 7
"	632	899 9	"	664	899 8
"	633	899 8	"	665	899 9
"	634	899 8	"	666	899 8
4/21/24	635	899 9	"	667	899 8
"	636	899 9	5/1/24	668	899 8
"	637	899 9	"	669	899 8
"	638	899 8	"	670	899 7
4/22/24	639	899 8	"	671	899 8

ASSAYER'S REGISTER OF GOLD INGOTS.

5 samples to each "melt"

DATE.	NO. OF MELT.		FINESS.	DATE.	NO. OF MELT.	FINESS.
1924.				1924		
5/1/24	672		899 9	5/8/24	704	899 8
5/2/24	673		899 7	"	705	899 8
	674	<i>From</i>	899 8	5/9/24	706	899 9
	675	<i>Remelt</i>	899 7	"	707	899 9
	676	<i>5/10/24</i>	899 7	"	708	899 8
5/2/24	677	<i>5/10/24</i>	899 9	"	709	899 8
"	678		899 9	"	710	899 8
"	679		900 0	"	711	899 8
"	680		899 9	"	712	899 8
"	681		899 9	"	713	899 9
"	682		899 9	5/12/24	714	900 0
5/2/24	683		899 9	"	715	900 0
"	684		899 8	"	716	899 9
"	685		899 9	"	717	899 9
"	686		899 7	"	718	899 9
5/6/24	687		899 9	5/13/24	719	899 9
"	688		899 9	"	720	899 9
"	689		899 8	"	721	899 9
5/7/24	690		899 8	"	722	899 9
5/6/24	691		899 7	"	723	899 9
"	692		899 8	5/14/24	724	899 8
5/7/24	693		899 9	"	725	899 8
"	694		899 9	"	726	899 9
"	695		900 0	"	727	899 8
"	696		899 7	"	728	899 8
"	697		899 7	5/16/24	729	900 0
"	698		899 8	"	730	899 8
"	699		899 9	"	731	899 9
5/8/24	700		899 9	"	732	899 8
"	701		899 9	"	733	899 9
"	702		899 9	5/17/24	734	900 0
"	703		899 8	"	735	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

5 samples to each 'Melt'

DATE	NO. OF MELT.	FINESS.	DATE	NO. OF MELT.	FINESS.
1924			1924		
5/17/24	736	899 9	5/24/24	768	899 8
"	737	899 9	"	769	899 8
"	738	899 8	"	770	899 8
"	739	899 9	"	771	899 9
"	740	899 9	"	772	899 9
"	741	899 9	5/27/24	773	899 9
"	742	899 8	"	774	899 9
"	743	899 8	"	775	899 8
5/19/24	744	899 9	"	776	899 8
"	745	899 8	"	777	899 9
"	746	899 9	5/28/24	778	900 0
"	747	899 9	"	779	899 9
"	748	899 9	"	780	900 0
5/21/24	749	899 8	"	781	900 0
"	750	899 8	"	782	899 9
"	751	899 8	"	783	900 0
"	752	899 8	"	784	900 0
"	753	899 8	"	785	900 0
5/22/24	754	899 9	"	786	899 9
"	755	899 8	"	787	899 9
"	756	899 9	5/29/24	788	899 9
"	757	899 8	"	789	899 9
"	758	From Remelt	"	790	900 0
5/23/24	759	900 0	"	791	899 9
"	760	899 9	"	792	899 9
"	761	899 9	5/31/24	793	899 9
"	762	899 8	"	794	900 0
5/24/24	763	900 0	"	795	899 8
5/25/24	764	899 9	"	796	899 8
"	765	899 8	"	797	900 0
"	766	900 9	6/2/24	798	899 9
"	767	899 9	"	799	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each "Kelt."

DATE.	NO. OF MELT.	FINER.	DATE.	NO. OF MELT.	FINER.	
1924			1924			
6/2/24	800	899 8	6/10/24	832	899 8	
"	801	899 9	6/11/24	833	899 9	
"	802	899 9	"	834	899 9	
6/3/24	803	899 9	"	835	900 0	
"	804	899 9	"	836	899 9	
"	805	899 9	"	837	899 8	
"	806	899 9	6/13/24	838	899 8	
"	807	899 9	"	839	899 7	From Remelt
6/5/24	808	899 9	"	840	899 8	
"	809	899 9	"	841	899 9	
"	810	899 9	"	842	899 9	
"	811	899 9	6/16/24	843	899 7	
"	812	899 8	"	844	899 8	
6/6/24	813	899 9	"	845	899 9	
"	814	899 8	"	846	899 8	
"	815	899 9	"	847	899 8	
"	816	899 8	"	848	899 8	
"	817	899 8	"	849	899 8	
6/7/24	818	899 8	"	850	899 8	
"	819	899 9	"	851	899 8	
"	820	899 8	"	852	899 8	
"	821	899 9	6/17/24	853	899 8	
"	822	899 8	"	854	899 9	
6/9/24	823	899 9	"	855	899 8	
"	824	899 8	"	856	899 8	
"	825	899 8	"	857	899 8	
"	826	899 9	"	858	899 8	
"	827	899 9	6/27/24	859	899 7	R. M.
6/10/24	828	900 0	6/26/24	860	899 8	From Remelt
"	829	899 9	"	861	899 9	"
"	830	899 9	"	862	899 9	"
"	831	899 8	2/27/24	863	900 0	R. M.

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each "Melt."

DATE.	No. OF MELT.		FINESS.	DATE.	No. OF MELT.	FINESS.
1924						
6/27/24	864	R. M.	900 0		896	
"	865	R. M.	900 0		897	
"	866	R. M.	899 7		898	
"	867		899 7		899	
"	868		899 7		900	
6/26/24	869		899 8		901	
"	870		899 8		902	
"	871		899 8		903	
"	872		899 8		904	
6/27/24	873		899 9		905	
	874				906	
	875				907	
	876				908	
	877				909	
	878				910	
	879				911	
	880				912	
	881				913	
	882				914	
	883				915	
	884				916	
	885				917	
	886				918	
	887				919	
	888				920	
	889				921	
	890				922	
	891				923	
	892				924	
	893				925	
	894				926	
	895				927	

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each "milk"

DATE	No. OF MELT.	FINESS.	DATE	No. OF MELT.	FINESS.
1924			1924		
Aug 7	1	899 8	8/18/24	33	899 9
"	2	899 9	"	34	899 8
"	3	899 8	8/19/24	35	899 8
"	4	899 8	"	36	899 8
" 8	5	899 8	"	37	899 9
"	6	899 8	"	38	899 8
"	7	899 9	"	39	899 8
"	8	899 8	"	40	899 8
" 11	9	900 0	"	41	899 9
"	10	900 0	"	42	899 8
"	11	900 0	"	43	899 9
"	12	900 0	"	44	899 9
"	13	899 9	8/22/24	45	899 8
"	14	899 8	"	46	899 8
" 12	15	900 0	"	47	899 8
"	16	899 9	"	48	899 9
"	17	899 9	"	49	899 9
"	18	899 9	"	50	899 8
" 13	19	899 9	"	51	900 0
"	20	899 9	"	52	900 0
"	21	899 8	8/23/24	53	899 9
"	22	899 9	"	54	899 8
" 14	23	899 9	"	55	899 8
"	24	899 9	"	56	899 9
"	25	899 8	8/24/24	57	899 8
"	26	899 8	"	58	899 8
" 15	27	899 9	"	59	899 8
"	28	899 9	"	60	899 8
"	29	899 9	"	61	899 8
"	30	899 9	"	62	899 8
" 18	31	899 8	8/27/24	63	899 9
"	32	899 8	"	64	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Receipts with each Melt

DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1924			1924		
8/27/24	65	899 9	9/9/24	97	900 0
"	66	899 8	"	98	899 8
8/28/24	67	899 8	9/10/24	99	899 9
"	68	899 8	"	100	899 9
"	69	899 8	"	101	899 9
"	70	899 8	"	102	900 0
8/29/24	71	899 9	"	103	899 8
"	72	899 8	"	104	899 9
"	73	899 9	"	105	900 0
"	74	899 9	"	106	900 0
8/30/24	75	899 9	9/11/24	107	899 9
"	76	899 9	"	108	899 9
"	77	900 0	"	109	899 8
"	78	900 0	"	110	899 8
9/2/24	79	900 0	9/13/24	111	899 9
"	80	899 9	"	112	899 9
9/3/24	81	900 0	"	113	899 9
"	82	899 9	"	114	899 9
"	83	899 9	9/16/24	115	900 0
"	84	899 9	"	116	899 9
9/4/24	85	899 8	"	117	899 9
"	86	900 0	"	118	899 9
"	87	899 9	"	119	899 8
"	88	899 8	"	120	899 8
9/6/24	89	899 9	9/18/24	121	899 9
"	90	899 8	"	122	899 8
"	91	899 9	"	123	899 8
"	92	899 9	"	124	899 9
9/8/24	93	899 9	"	125	899 9
"	94	899 9	"	126	899 9
"	95	899 9	9/19/24	127	899 9
"	96	899 9	"	128	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each "Melt"

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1924 9/19/24	129	900 0	1924 161	130	900 —
	130	899 9		162	899 9
	131	899 8		163	899 9
	132	899 8		164	899 8
9/20/24	133	899 8	12/27/24	165	899 8
"	134	899 8	"	166	899 9
"	135	899 8	"	167	899 9
"	136	899 9	12/29/24	168	899 9
"	137	899 9	"	169	899 9
"	138	899 8	"	170	899 9
"	139	900 0	"	171	899 9
"	140	900 0	"	172	899 9
9/23/24	141	899 9	12/31/24	173	899 9
"	142	899 9	"	174	899 9
"	143	899 9	"	175	899 1
"	144	899 8	12/31/24	176	899 9
"	145	899 8	"	177	899 9
"	146	899 8	"	178	899 9
"	147	899 9	"	179	899 9
"	148	899 8	"	180	899 9
12/22/24	149	899 9	1/2/25	181	899 9
"	150	899 8	"	182	899 9
"	151	899 9	"	183	899 9
"	152	899 8	"	184	899 9
"	153	899 9	"	185	899 9
12/23/24	154	899 8	"	186	899 9
"	155	899 8	"	187	899 9
"	156	899 9	1/6/25	188	900 —
"	157	899 9	"	189	899 9
"	158	899 9	"	190	900 —
12/24/24	159	899 9	"	191	899 9
"	160	899 8	1/6/25	192	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each Melt

DATE. 1925	No. OF MELT.	FINESS.	DATE. 1925	No. OF MELT.	FINESS.
1/6/25	193	899 9	1/13/25	225	899 9
"	4	899 9	1/14/25	6	900 -
"	5	899 9	"	7	899 9
"	6	899 9	"	8	900 -
"	7	899 9	1/15/25	9	899 9
"	8	899 8	"	230	899 9
"	9	899 9	"	1	899 9
1/7/25	300	899 9	"	2	899 9
"	1	899 9	"	3	900 -
"	2	899 9	1/16/25	4	899 9
"	3	899 9	"	5	899 9
1/8/25	4	899 9	"	6	899 9
"	5	899 9	"	7	899 8
"	6	899 9	"	8	899 9
"	7	899 9	1/17/25	9	899 9
1/9/25	8	899 9	"	240	899 9
"	9	899 9	"	1	899 9
"	210	899 9	"	2	899 8
"	1	899 9	"	3	899 8
1/10/25	2	900 -	1/20/25	4	899 8
"	3	899 9	"	5	899 9
"	4	899 9	"	6	899 8
"	5	899 9	"	7	899 9
1/12/25	6	899 9	"	8	899 8
"	7	900 -	"	9	899 9
"	8	899 9	"	250	899 8
"	9	899 9	"	1	899 8
"	220	899 9	"	2	899 8
1/13/25	1	900 -	"	3	899 8
"	2	900 -	1/22/25	4	899 9
"	3	899 9	"	5	899 9
"	4	899 9	"	6	899 8

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each "Melt"

DATE	NO. OF MELT.	FINESS.	DATE	NO. OF MELT.	FINESS.
1925			1925		
1/22/25	257	899	8-1/28/25	289	899 9
"	8	899	8-1/30/25	290	899 8
1/24/25	9	900	"	291	899 7
"	260	900	"	292	899 8
"	1	899	"	293	899 8
"	2	899	1/31/25	294	899 7
"	3	899	"	295	899 8
"	4	899	"	296	899 8
"	5	899	"	297	899 8
"	6	899	2/3/25	298	899 8
"	7	899	"	299	899 7
"	8	899	"	300	899 9
1/26/25	9	900	"	301	899 8
"	270	899	2/4/25	302	899 8
"	1	900	"	303	899 7
"	2	899	"	304	899 7
"	3	899	"	305	899 8
"	4	899	"	306	899 7
"	5	899	"	307	899 5
"	6	899	2/6/25	308	899 7
"	7	899	"	309	899 7
1/27/25	8	899	"	310	899 7
"	9	899	"	311	899 7
"	280	899	"	312	899 7
"	1	899	"	313	899 8
1/28/25	2	899	"	314	899 8
"	3	899	"	315	899 8
"	4	899	"	316	899 9
"	5	900	"	317	899 8
1/29/25	6	899	"	318	899 7
"	7	899	"	319	899 7
"	8	899	2/7/25	320	899 8

from bank

*Remelted
twice*

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each Melt.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1925			1925		
2/7/25	321	899 9	2/12/25	353	899 8
"	322	899 9	"	354	899 9
"	323	899 9	2/16/25	355	899 8
"	324	899 8	"	356	899 9
"	325	899 8	"	357	899 9
2/9/25	326	899 8	"	358	899 9
"	327	899 8	"	359	899 8
"	328	899 8	"	360	899 8
"	329	899 9	"	361	899 8
"	330	899 8	"	362	899 9
"	331	899 9	"	363	899 9
2/11/25	332	899 9	"	364	899 9
"	333	899 9	"	365	899 8
"	334	899 8	2/17/25	366	899 9
"	335	899 8	"	367	899 9
"	336	899 8	"	368	899 8
"	337	899 8	"	369	899 9
"	338	899 8	"	370	899 8
2/12/25	339	899 9	"	371	899 8
"	340	899 8	"	372	899 9
"	341	899 8	"	373	899 9
"	342	899 8	"	374	900 —
"	343	899 7	"	375	899 9
"	344	899 7	"	376	899 9
"	345	899 9	"	377	899 9
"	346	899 8	2/19/25	378	899 9
"	347	899 9	"	379	899 9
"	348	899 8	"	380	900 —
"	349	899 8	"	381	899 8
"	350	899 8	"	382	900 —
"	351	899 8	"	383	899 9
"	352	899 8	2/20/25	384	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each Melt.

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
<i>1925</i>			<i>1925</i>		
<i>2/20/25</i>	<i>385</i>	<i>899 9</i>	<i>2/27/25</i>	<i>417</i>	<i>899 8</i>
"	<i>386</i>	<i>899 8</i>	"	<i>418</i>	<i>899 9</i>
"	<i>387</i>	<i>899 9</i>	"	<i>419</i>	<i>899 9</i>
"	<i>388</i>	<i>899 9</i>	<i>3/2/25</i>	<i>420</i>	<i>899 8</i>
"	<i>389</i>	<i>899 9</i>	"	<i>421</i>	<i>899 9</i>
"	<i>390</i>	<i>899 9</i>	"	<i>422</i>	<i>899 8</i>
"	<i>391</i>	<i>899 9</i>	<i>3/3/25</i>	<i>423</i>	<i>899 9</i>
"	<i>392</i>	<i>900 —</i>	"	<i>424</i>	<i>899 9</i>
"	<i>393</i>	<i>900 —</i>	"	<i>425</i>	<i>899 8</i>
"	<i>394</i>	<i>899 8</i>	"	<i>426</i>	<i>899 9</i>
"	<i>395</i>	<i>899 8</i>	"	<i>427</i>	<i>899 8</i>
<i>2/24/25</i>	<i>396</i>	<i>899 8</i>	"	<i>428</i>	<i>899 9</i>
"	<i>397</i>	<i>899 8</i>	<i>3/4/25</i>	<i>429</i>	<i>899 8</i>
"	<i>398</i>	<i>899 9</i>	"	<i>430</i>	<i>899 9</i>
"	<i>399</i>	<i>899 9</i>	"	<i>431</i>	<i>899 9</i>
"	<i>400</i>	<i>899 9</i>	<i>3/5/25</i>	<i>432</i>	<i>899 9</i>
"	<i>401</i>	<i>899 8</i>	"	<i>433</i>	<i>899 9</i>
<i>2/25/25</i>	<i>402</i>	<i>899 8</i>	"	<i>434</i>	<i>900 —</i>
"	<i>403</i>	<i>899 8</i>	<i>3/7/25</i>	<i>435</i>	<i>899 9</i>
"	<i>404</i>	<i>899 8</i>	"	<i>436</i>	<i>899 8</i>
"	<i>405</i>	<i>899 9</i>	"	<i>437</i>	<i>899 8</i>
"	<i>406</i>	<i>899 9</i>	<i>3/8/25</i>	<i>438</i>	<i>899 8</i>
"	<i>407</i>	<i>899 9</i>	"	<i>439</i>	<i>899 9</i>
"	<i>408</i>	<i>899 9</i>	"	<i>440</i>	<i>899 9</i>
"	<i>409</i>	<i>899 9</i>	<i>3/11/25</i>	<i>441</i>	<i>899 8</i>
"	<i>410</i>	<i>899 9</i>	"	<i>442</i>	<i>899 8</i>
"	<i>411</i>	<i>899 9</i>	"	<i>443</i>	<i>899 8</i>
"	<i>412</i>	<i>899 8</i>	"	<i>444</i>	<i>899 9</i>
"	<i>413</i>	<i>899 8</i>	"	<i>445</i>	<i>899 9</i>
<i>2/27/25</i>	<i>414</i>	<i>899 8</i>	<i>3/12/25</i>	<i>446</i>	<i>899 8</i>
"	<i>415</i>	<i>899 9</i>	"	<i>447</i>	<i>899 8</i>
"	<i>416</i>	<i>899 8</i>	"	<i>448</i>	<i>899 9</i>

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Draples to each "Melk"

DATE. 1925	No. OF MELT. 1925	FINENESS.	DATE.	No. OF MELT.	FINENESS.
3/12/25	449	899 9	481	3/16/25	899 8
"	450	899 9	482	"	899 9
"	451	899 9	483	"	899 9
"	452	899 9	484	"	899 9
"	453	899 9	485	"	899 9
"	454	899 9	486	3/18/25	899 9
"	455	899 8	487	"	899 9
"	456	899 9	488	"	899 8
"	457	899 9	489	"	899 8
3/14/25	458	899 9	490	"	899 8
"	459	899 9	491	"	899 8
"	460	899 9	492	3/19/25	899 8
"	461	899 9	493	"	899 8
"	462	899 9	494	"	899 8
"	463	899 9	495	"	899 8
3/16/25	464	899 9	496	"	899 9
"	465	899 8	497	"	899 8
"	466	899 8	498	3/20/25	899 9
"	467	899 8	499	"	899 9
"	468	899 9	500	"	899 9
"	469	900 —	501	"	899 9
"	470	899 9	502	"	899 9
"	471	899 9	503	"	899 9
"	472	899 8	504	3/24/25	899 9
"	473	899 8	505	"	899 9
"	474	899 8	506	"	899 9
"	475	899 9	507	"	899 8
"	476	899 8	508	"	899 8
"	477	899 8	509	"	899 9
"	478	899 8	510	3/23/25	899 8
"	479	899 9	511	"	899 8
"	480	899 8	512	"	899 8

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each "Melt"

DATE	NO. OF MELT.	FINENESS.	DATE	NO. OF MELT.	FINENESS.
1925			1925		
3-23-25	513	899 9	3/28	545	899 9
"	514	899 8	3/30	546	899 9
"	515	899 9	"	547	899 9
3/24/25	516	899 9	"	548	899 8
"	517	899 9	"	549	899 9
"	518	899 8	"	550	899 9
"	519	899 9	"	551	899 8
"	520	899 8	4/1/25	552	899 8
"	521	899 8	"	553	899 8
3/25/25	522	899 8	"	554	899 8
"	523	899 9	"	555	899 8
"	524	899 9	"	556	899 9
"	525	899 9	"	557	899 9
"	526	900 0	"	558	899 9
"	527	899 7	"	559	899 9
3/26/25	528	899 9	4/2/25	560	899 9
"	529	899 9	"	561	899 8
"	530	899 8	"	562	899 9
"	531	899 8	"	563	899 8
"	532	899 8	"	564	899 8
"	533	899 9	"	565	899 8
3/27/25	534	899 9	"	566	899 9
"	535	899 8	4/3/25	567	899 9
"	536	899 9	"	568	899 9
"	537	899 8	"	569	900 -
"	538	899 9	4/4/25	570	899 8
"	539	899 9	"	571	899 9
3/28/25	540	899 9	"	572	899 9
"	541	899 9	4/6/25	573	899 8
"	542	899 8	"	574	899 8
"	543	899 8	"	575	899 8
"	544	899 9	4/7/25	576	899 7

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each "Melt"

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1925					
4/7/25	577	899 8	4/14/25	609	899 9
"	578	899 8	"	610	899 8
"	579	899 9	"	611	900 —
"	580	899 9	4/15/25	612	899 9
"	581	899 9	"	613	900 —
4/8/25	582	899 8	"	614	899 8
"	583	899 9	"	615	900 —
"	584	899 8	"	616	900 —
"	585	899 8	"	617	899 9
"	586	899 9	"	618	899 8
"	587	899 9	"	619	899 8
4/9/25	588	899 9	"	620	899 9
"	589	899 9	"	621	899 9
"	590	899 9	"	622	899 8
"	591	899 9	"	623	899 8
"	592	899 9	4/17/25	624	899 8
"	593	899 9	"	625	899 8
4/10/25	594	899 8	"	626	899 9
"	595	899 8	"	627	899 8
"	596	899 8	"	628	899 9
"	597	899 8	"	629	899 9
"	598	899 8	"	630	899 8
"	599	899 9	"	631	899 9
4/11/25	600	899 8	"	632	899 8
"	601	899 8	"	633	899 8
"	602	899 8	"	634	899 9
"	603	899 8	"	635	899 9
"	604	899 8	4/18/25	636	899 9
"	605	899 8	"	637	899 8
4/14/25	606	899 8	"	638	899 8
"	607	899 9	"	639	899 8
"	608	899 9	"	640	899 9

ASSAYER'S REGISTER OF GOLD INGOTS.

2-2280

5 Samples to each "Melt"

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1925					
4/18/25	641	899 9	4/27/25	673	899 8
4/20/25	642	899 8	"	674	899 8
"	643	899 8	"	675	899 9
"	644	899 8	"	676	899 8
"	645	899 8	"	677	899 8
"	646	899 8	"	678	899 9
"	647	899 9	"	679	899 9
4/21/25	648	899 8	"	680	899 8
"	649	899 9	"	681	899 8
"	650	899 8	"	682	899 9
"	651	899 8	4/28/25	683	899 8
"	652	899 9	"	684	899 7
"	653	899 8	"	685	899 8
4/22/25	654	899 8	"	686	899 8
"	655	899 9	4/30/24	687	899 7
"	656	899 8	"	688	899 8
"	657	899 8	"	689	899 8
"	658	899 8	"	690	899 7
"	659	899 9	"	691	899 8
4/24/25	660	899 9	"	692	899 8
"	661	899 9	"	693	899 8
"	662	899 8	"	694	899 7
"	663	899 8	5/1/25	695	899 9
"	664	899 9	"	696	899 8
"	665	899 8	"	697	899 9
"	666	899 8	"	698	899 8
"	667	899 8	"	699	899 9
"	668	900 -	"	700	899 8
"	669	899 8	"	701	899 9
"	670	899 8	"	702	899 8
"	671	899 8	5/4/25	703	899 9
4/27/25	672	899 8	"	704	899 8

Romelt

ASSAYER'S REGISTER OF GOLD INGOTS.

50 samples to each "Melt"

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
1925			1925		
5/4/25	705	899 9		737	899 9
"	706	899 8		738	899 9
"	707	899 9		739	899 9
5/6/25	708	900 -		740	899 9
"	709	899 9	5/14/25	741	899 9
"	710	899 8		742	899 8
"	711	899 9		743	899 9
"	712	899 9		744	899 8
"	713	899 9		745	899 8
"	714	899 7		746	899 8
"	715	899 9		747	899 7
"	716	899 8		748	899 8
"	717	899 9		749	899 8
"	718	899 9		750	899 8
5/9/25	719	899 8		751	899 9
	720	899 9		752	899 8
	721	899 9		753	899 8
	722	899 9	5/19/25	754	899 8
	723	899 8	"	755	899 9
	724	899 9	5/15/25	756	899 8
	725	899 8		757	899 8
	726	900 -		758	899 8
	727	899 9		759	899 9
	728	899 8		760	899 8
	729	899 9		761	899 8
	730	900 0		762	899 7
	731	900 -	5/19/25	763	899 8
	732	899 9	"	764	899 8
	733	899 9	"	765	899 8
	734	899 8	"	766	899 8
	735	899 8	"	767	899 8
	736	899 8	"	768	899 8

Non-Random

" "

ASSAYER'S REGISTER OF GOLD INGOTS.

5 Samples to each "Melt"

DATE.	NO. OF MELT.	FINENESS.	DATE.	NO. OF MELT.	FINENESS.
<i>1925</i>					
<i>5/20/25</i>	<i>769</i>	<i>899</i>	<i>5/26/25</i>	<i>801</i>	<i>899</i>
"	<i>770</i>	<i>899</i>	"	<i>802</i>	<i>899</i>
<i>5/21/25</i>	<i>771</i>	<i>899</i>	"	<i>803</i>	<i>899</i>
<i>5/20/25</i>	<i>772</i>	<i>899</i>	"	<i>804</i>	<i>899</i>
"	<i>773</i>	<i>899</i>	"	<i>805</i>	<i>899</i>
"	<i>774</i>	<i>899</i>	"	<i>806</i>	<i>899</i>
<i>5/21/25</i>	<i>775</i>	<i>899</i>	"	<i>807</i>	<i>899</i>
"	<i>776</i>	<i>899</i>	"	<i>808</i>	<i>899</i>
"	<i>777</i>	<i>899</i>	"	<i>809</i>	<i>899</i>
"	<i>778</i>	<i>899</i>	"	<i>810</i>	<i>899</i>
"	<i>779</i>	<i>899</i>	<i>5/29/25</i>	<i>811</i>	<i>899</i>
"	<i>780</i>	<i>899</i>	"	<i>812</i>	<i>899</i>
"	<i>781</i>	<i>899</i>	"	<i>813</i>	<i>899</i>
"	<i>782</i>	<i>899</i>	"	<i>814</i>	<i>899</i>
<i>5/23/25</i>	<i>783</i>	<i>899</i>	"	<i>815</i>	<i>899</i>
"	<i>784</i>	<i>899</i>	"	<i>816</i>	<i>899</i>
"	<i>785</i>	<i>899</i>	"	<i>817</i>	<i>899</i>
"	<i>786</i>	<i>899</i>	"	<i>818</i>	<i>899</i>
"	<i>787</i>	<i>899</i>	"	<i>819</i>	<i>899</i>
"	<i>788</i>	<i>899</i>	"	<i>820</i>	<i>899</i>
"	<i>789</i>	<i>899</i>	<i>6/1/25</i>	<i>821</i>	<i>899</i>
"	<i>790</i>	<i>899</i>	"	<i>822</i>	<i>899</i>
"	<i>791</i>	<i>899</i>	"	<i>823</i>	<i>899</i>
"	<i>792</i>	<i>899</i>	"	<i>824</i>	<i>899</i>
<i>5/26/25</i>	<i>793</i>	<i>899</i>	"	<i>825</i>	<i>899</i>
"	<i>794</i>	<i>899</i>	"	<i>826</i>	<i>899</i>
<i>5/28/25</i>	<i>795</i>	<i>899</i>	<i>6/3/25</i>	<i>827</i>	<i>899</i>
"	<i>796</i>	<i>899</i>	"	<i>828</i>	<i>899</i>
"	<i>797</i>	<i>900</i>	"	<i>829</i>	<i>899</i>
"	<i>798</i>	<i>899</i>	"	<i>830</i>	<i>899</i>
<i>5/26/25</i>	<i>799</i>	<i>899</i>	"	<i>831</i>	<i>899</i>
"	<i>800</i>	<i>899</i>	"	<i>832</i>	<i>899</i>

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1926					
2/10	33	899 9			
	34	899 9			
	35	899 9			
	36	899 8			
2/11	37	899 8			
	38	899 9			
	39	899 9			
	40	899 9			
2/12	1	899 9			
	2	899 9			
	3	899 9			
	4	899 9			
2/12	5	899 8			
	6	899 9			
	7	899 9			
	8	899 9			
2/15	9	899 9			
	50	899 8			
	1	899 9			
	2	899 9			
2/16	3	899 9			
	4	899 8			
	5	899 8			
	6	899 9			
	7	899 9			
2/17	8	899 9			
	9	899 9			
	60	899 9			
	1	899 9			
	2	899 9			
2/18	3	899 9			
	4	899 9			

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE.	NO. OF MELT.	FINESS.	DATE.	NO. OF MELT.	FINESS.
1926			1926		
2/18	65	899 9	3/1	97	899 8
	6	899 9		8	899 9
2/19	7	899 9		9	899 9
	8	899 9	100		900 0
	9	899 9	3/2	1	899 9
	70	899 9		2	899 8
2/20	1	899 9		3	899 9
	2	899 9		4	899 9
	3	899 9		5	899 9
	4	899 9	3/3	6	899 9
2/23	5	899 9		7	899 9
	6	899 9		8	899 9
	7	899 9		9	899 9
	8	899 9	110		899 9
2/24	9	899 8	4/12	1	899 9
	80	899 9		2	899 9
	1	899 9		3	900 0
	2	899 9		4	900 0
	3	899 9		5	900 0
2/25	4	899 9		6	899 9
	5	899 9		7	
	6	899 9		8	
	7	899 8		9	
	8	899 9	120		
2/26	9	899 9		1	
	90	899 9		2	
	1	899 9		3	
	2	899 9		4	
2/27	3	899 9		5	
	4	899 9		6	
	5	899 9		7	
	6	899 9		8	

ASSAYER'S REGISTER OF GOLD INGOTS.


2-2229


DATE.	No. OF MELT.	FINENESS.	DATE.	No. OF MELT.	FINENESS.
1927			1927		
6/2	1	900 0	8/17	24	900 0
	2	899 9		5	899 9
	3	900 0		6	899 9
	4	900 0	8/19	7	899 9
	5	900 0		8	899 9
	6	900 0		9	899 9
6/16	7	899 9		30	900 0
	8	900 0		1	900 0
			8/20	2	899 9
8/8/27	1	899 8		3	899 9
	2	899 9	8/22	4	900 0
	3	900 0	6/13	5	899 9
	4	899 8		6	899 8
8/9	5	899 9		7	899 9
	6	899 9		8	
	7	899 9		9	
8/10	8	899 9		40	
	9	899 9		1	
	10	900 0		2	
8/11	1	899 8		3	
	2	899 9		4	
	3	900 0		5	
8/12	4	899 9		6	
	5	900 0		7	
	6	899 9		8	
8/13	7	900 0		9	
	8	900 0		50	
	9	900 0		1	
8/16	20	900 0		2	
	1	900 0		3	
	2	900 0		4	
	3	899 9		5	

ASSAYER'S REGISTER OF GOLD INGOTS.

DATE	No. OF MELT.	FINENESS.	DATE	No. OF MELT.	FINENESS.
1929					
June 6	1	899 8			
	2	899 8			
1930					
June 9	1	899 8			
	2	899 8			
	3	899 9			
	4	899 8			

ASSAYER'S REGISTER OF GOLD INGOTS.







Assayer's Register of Gold Ingots, 1906-1907

